



Fabrication and Evaluation of porous SiC

Iwasa, Yoshimi; Lu, Weifang; Teramae, Fumiharu; Kamiyama, Satoshi; Ou, Haiyan; Takeuchi, Tetsuya; Iwaya, Motoaki; Akasaki, Isamu

Publication date:
2016

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Iwasa, Y., Lu, W., Teramae, F., Kamiyama, S., Ou, H., Takeuchi, T., Iwaya, M., & Akasaki, I. (2016). *Fabrication and Evaluation of porous SiC*. Abstract from 2016 E-MRS Fall Meeting and Exhibit, Warsaw, Poland.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

START AT	SUBJECT	View All	NUM.	ADD
10:15	Fabrication and Evaluation of porous SiC intentional doped B-N	~	D.11.6	☆
<p>Authors : Yoshimi Iwasa, Weifang Lu, Fumiharu Teramae, Satoshi Kamiyama, Haiyan Ou, Tetsuya Takeuchi, Motoaki Iwaya, Isamu Akasaki</p> <p>Affiliations : Department of Materials Science and Engineering, Meijo University, 1-501 Shiogamaguchi, Tenpaku-ku, Nagoya 468-8502, Japan; Yoshimi Iwasa, Satoshi Kamiyama, Tetsuya Takeuchi, Motoaki Iwaya, Isamu Akasaki. Department of Photonics Engineering, Technical University of Denmark, DK-2800. Lyngby, Denmark; Weifang Lu, Haiyan Ou. ELSEED Corp., Innovative Science and Technology Building 2F, Meijo University, 2-1522 Shiogamaguchi, Tenpaku-ku, Nagoya 468-0073, Japan; Fumiharu Teramae.</p> <p>Resume : White LEDs with high color rendering index (CRI) are greatly demanded in general lighting applications. However, current major white LEDs composed of blue LED and yellow phosphor still have insufficient CRI, because of the lack of green and red color components. In this study, we present a new solid state phosphor material, porous SiC, which contains donor and acceptor impurities to create donor-acceptor-pair (DAP) recombination. Since this material can emit continuous visible spectrum similar to sun light, it is possible to fabricate high quality white LEDs with high CRI. Recently, we confirmed that DAP emission is enhanced and the peak wavelength is shifted to green-blue side due to the quantum size effect in porous SiC from a commercial n-type 6H-SiC substrate containing N (donor) and B (acceptor). In addition, it was reported that a non-radiative surface recombination was inhibited by specific surface passivation on porous SiC, while it has wider surface with problematic non-radiative surface recombination [1]. However, emission efficiency of such porous SiC is still low because of low B concentration of approximately 1x10¹⁷ cm-3. In this study, we investigate an impact of doping concentrations of N and B on emission efficiency of porous SiC. As a method fabricating porous SiC, SiC samples are etched by anodic oxidation technique with a hydrofluoric acid solution. Moreover, as a passivation technique, Al2O3 deposited by atomic layer deposition (ALD) technique and annealed at a low temperature. The porous SiC after Al2O3 passivation has a broad blue-green light PL emission with a peak wavelength of 507nm, and the full width half maximum (FWHM) of 138.6nm. Compared with the porous SiC from commercial n-type substrate, the sample produced from intentionally codoped SiC has 2.63 times larger PL intensity. The result may show that the porous SiC with a combination of the bulk N and B codoped SiC is a promising candidate to generate high quality white light with a high CRI. References [1] Weifang Lu, et al. "Photoluminescence enhancement in porous SiC passivated by atomic layer deposited Al2O3" CLEO 6-192 (2016).</p>				